

AN 2000:293852 HCAPLUS
 DN 132:282768
 TI Manufacture of low-melting-point and low-vapor-pressure powdered braze for brazing stainless steel
 IN Zhang, Shaoming; Xu, Zhutian; Li, Yongwei; Shi, Likai; Xing, Jifeng; Guo, Hong; Zhu, Xuexin; He, Huijun; Li, Keping; Wang, Jinlei
 PA Beijing Non-Ferrous Metal Research General Institute, Peop. Rep. China
 SO Faming Zhuanli Shenqing Gongkai Shuomingshu, 9 pp.
 CODEN: CNXXEV
 DT Patent
 LA Chinese
 FAN.CNT 1

| | PATENT NO. | KIND | DATE | APPLICATION NO. | DATE |
|------|----------------|------|----------|-----------------|----------|
| PI | CN 1205260 | A | 19990120 | CN 1998-101071 | 19980401 |
| | CN 1075416 | B | 20011128 | | |
| PRAI | CN 1998-101071 | | 19980401 | | |

AB The braze contains Ag 2.0-8.0, Cu 0.20-1.50, Cr 0.10-0.60%, and Sn balance. The braze is manufd. by melting a mixt. of Sn, Ag, Cu, and CuCr13 at 400-500.degree. in an inert atm., casting into ingots, remelting the ingots at 400-500.degree. in an inert atm., and atomizing with an inert gas at 1.5-3.0 MPa. The inert gas is N2 or Ar.